## Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

## Listing of Claims:

- 1 Claim 1 (previously presented): A flexible, hollow waveguide for transmitting
- 2 radiation in visible and IR regions, comprising:
- 3 (a) a hollow, flexible tube having a transparent annular body defining a bore
- 4 with a smooth inner bore surface;
  - (b) a reflective metal layer disposed upon the smooth inner bore surface; and
- 6 (c) a composite of dielectric, sulfide-containing materials having a high
- 7 refractive index ratio, said sulfide-containing materials disposed upon said reflective
- 8 metal layer and forming a photonic, bandgap tube transmitting in the visible and IR
- 9 regions.

5

- 1 Claim 2 (original): The waveguide in accordance with claim 1, wherein said hollow,
- 2 flexible tube is composed of glass.
- 1 Claim 3 (original): The waveguide in accordance with claim 1, wherein said hollow,
- 2 flexible glass tube is composed of silica-glass.

- 1 Claim 4 (original): The waveguide in accordance with claim 1, wherein said
- 2 composite of dielectric, sulfide-containing materials comprise disparate refractive
- 3 indices of approximately 2:1.
- 1 Claim 5 (original): The waveguide in accordance with claim 4, wherein said metallic
- 2 layer is selected from a group of metals consisting of: Ag, Au, Cu, Pt, Ni, Mb, Al, and
- 3 combinations thereof.
- 1 Claim 6 (original): The waveguide in accordance with claim 1, further comprising:
- 2 (d) an outer layer surrounding the hollow, flexible tube.
- 1 Claim 7 (previously presented): The waveguide in accordance with claim 4, wherein
- the composite of sulfide-containing materials respectively comprise paired composite
- 3 layers of cadmium sulfide and lead sulfide.
- 1 Claim 8 (previously presented): The waveguide of claim 4, wherein said outer layer
- 2 is composed of a material selected from a group of materials consisting of plastic,
- 3 and silicone.
- 1 Claim 9 (previously presented): A flexible, hollow waveguide, comprising:
- 2 (a) a flexible, hollow tube having a transparent annular body defining a bore
- 3 with a smooth inner bore surface;
- 4 (b) a metallic layer disposed upon the smooth inner bore surface; and

- 5 (c) a composite of dielectric materials disposed upon the metallic layer
- 6 featuring disparate refractive indices with a ratio of approximately 2.1, wherein the
- 7 composite of dielectric materials form sulfide-containing layers.
- 1 Claim 10 (previously presented): The waveguide in accordance with claim 9, wherein
- 2 said composite of dielectric materials respectively comprise two sulfide-containing
- 3 layers.
- 1 Claim 11 (original): The waveguide in accordance with claim 9, wherein said metallic
- 2 layer is selected from a group of metals consisting of: Ag, Au, Cu, Pt, Ni, Mb, Al, and
- 3 combinations thereof.
- 1 Claim 12 (previously presented): The waveguide in accordance with claim 9, further
- 2 comprising:
- 3 (d) an outer layer surrounding the hollow flexible tube.
- 1 Claim 13 (canceled).
- 1 Claim 14 (previously presented): The waveguide in accordance with claim 9, wherein
- 2 the composite of dielectric materials respectively comprise cadmium sulfide and lead
- 3 sulfide.

- 1 Claim 15 (previously presented): The waveguide in accordance with claim 11,
- 2 wherein said outer layer is selected from a group of materials consisting of plastic,
- 3 and silicone.
- 1 Claim 16 (previously presented): A flexible, hollow waveguide for transmitting
- 2 radiation in visible and IR regions, comprising:
- 3 (a) a hollow, flexible tube having a transparent annular body defining a bore
- 4 with a smooth inner bore surface; and
- 5 (b) a composite of dielectric, paired sulfide-containing materials having a high
- 6 refractive index ratio, said sulfide-containing materials disposed upon said hollow
- 7 tube, and forming a photonic, bandgap tube transmitting in the visible and IR
- 8 regions.
- 1 Claim 17 (previously presented): The waveguide in accordance with claim 16,
- 2 wherein said hollow, flexible tube is composed of glass.
- 1 Claim 18 (previously presented): The waveguide in accordance with claim 16,
- 2 wherein said hollow, flexible glass tube is composed of silica-glass.
- 1 Claim 19 (previously presented): The waveguide in accordance with claim 16,
- 2 wherein said composite of dielectric, sulfide-containing materials comprise disparate
- 3 refractive indices of approximately 2:1.

- 1 Claim 20 (previously presented): The waveguide in accordance with claim 19, further
- 2 comprising:
- 3 (d) an outer layer surrounding the hollow, flexible tube.
- 1 Claim 21 (previously presented): The waveguide in accordance with claim 16,
- 2 wherein the composite of sulfide-containing materials respectively comprise paired
- 3 composite layers of cadmium sulfide and lead sulfide.
- 1 Claim 22 (previously presented): The waveguide of claim 20, wherein said outer
- 2 layer is composed of a material selected from a group of materials consisting of
- 3 plastic, and silicone.
- 1 Claim 23 (previously presented): A flexible, hollow waveguide, comprising:
- 2 (a) a flexible, hollow tube having a transparent annular body defining a bore
- 3 with a smooth inner bore surface; and
- 4 (b) a composite of dielectric materials disposed upon the smooth inner bore
- 5 surface of said transparent annular body, featuring disparate refractive indices with a
- 6 ratio of approximately 2.1, wherein said composite of dielectric materials respectively
- 7 comprise two sulfide layers.
- 1 Claim 24 (canceled).

- 1 Claim 25 (previously presented): The waveguide in accordance with claim 23, further
- 2 comprising:
- 3 (d) an outer layer surrounding the hollow flexible tube.
- 1 Claim 26 (previously presented): The waveguide in accordance with claim 23,
- 2 wherein the composite of dielectric materials respectively comprise cadmium sulfide
- 3 and lead sulfide.
- 1 Claim 27 (previously presented): The waveguide in accordance with claim 25,
- wherein said outer layer is selected from a group of materials consisting of plastic,
- 3 and silicone.
- 1 Claim 28 (previously presented): A method of fabricating a flexible, hollow
- 2 waveguide using liquid phase deposition, comprising the steps of:
- 3 (a) <u>depositing</u> a metallic layer on a smooth, inner bore surface of a hollow,
- 4 flexible, silica-glass tube; and
- 5 (b) depositing two sulfide-containing layers, cadmium sulfide and lead sulfide,
- 6 respectively, upon said metallic layer of step (a).
- 1 Claim 29 (canceled).
- 1 Claim 30 (canceled).

- Claim 31 (previously presented): A method of fabricating a flexible, hollow waveguide using liquid phase deposition, comprising the steps of:
- (a) depositing at first layer of cadmium sulfide upon an inner, smooth bore
  surface of a hollow silica-glass tube; and
- (b) depositing at least a second layer of lead sulfide over said first layer of
  cadmium sulfide.
- 1 Claim 32 (previously presented): The method in accordance with claim 31, wherein
- 2 multiple sulfide-containing layers of cadmium sulfide and lead sulfide, respectively,
- 3 are stack deposited upon said inner, smooth bore of said hollow tube.
- 1 Claim 33 (canceled).